


## AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application.

1. (original) A chemical composition comprising the formula:



wherein M is a platinum group metal; and

wherein x and y are positive numbers.

2. (original) The chemical composition of claim 1, wherein M is platinum.

3. (currently amended) The chemical composition of claim 2 ~~claim 1~~, wherein composition comprises ~~less than about 30%~~ greater than 0 to about 30 percent platinum in an amount greater than 0 to about 30 percent by weight.

4. (original) The chemical composition of claim 1,  
wherein x is about 1 to about 2; and  
wherein y is greater than 0 up to about 2.

5. (original) The chemical composition of claim 1, wherein the composition is combined with a conductive support.


6. (original) The chemical composition of claim 5, wherein the combination of the composition and the conductive support comprises at least 20% by weight of the conductive support.

7. (original) The chemical composition of claim 5, wherein the combination of the composition and the conductive support comprises at least 50% by weight of the conductive support.

8. (original) The chemical composition of claim 5, wherein the conductive support is carbon black.

9. (original) The chemical composition of claim 1, wherein the composition is substantially free of silica.
10. (original) An electrode comprising the chemical composition of claim 1.
11. (original) A device comprising:  
a cathode comprising a chemical composition comprising the formula:  
$$M-SnO_x \cdot yH_2O$$
  
wherein M is a platinum group metal; and  
wherein x and y are positive numbers;  
an anode capable of catalytically oxidizing hydrogen; and  
an electrolyte in contact with both the cathode and the anode.
12. (original) The device of claim 11, wherein the device is a fuel cell.
13. (original) The device of claim 11, wherein the cathode and the anode are on opposing surfaces of a proton-conducting membrane.
14. (original) The device of claim 13, wherein the proton-conducting membrane comprises a perfluorosulfonic acid polymer.
15. (original) A material comprising:  
a conductive support; and  
a chemical composition comprising the formula:  
$$M-SnO_x \cdot yH_2O$$
  
wherein M is a platinum group metal; and  
wherein x and y are positive numbers.
16. (original) The material of claim 15, wherein the conductive support is conductive carbon.

17. (original) A method of electrochemical reduction comprising the steps of:  
providing an a cathode comprising a chemical composition comprising the formula:



wherein M is a platinum group metal; and

wherein x and y are positive numbers;

providing an anode; and

contacting a substance to be reduced to the cathode.

18. (original) The method of claim 17, wherein the substance to be reduced is oxygen.